

2085A Polyurethane-based Biomedical Elastomer

Category : Polymer , Thermoset , Polyurethane, TS , Rubber or Thermoset Elastomer (TSE)

Material Notes:

Order this product through the following link:

http://www.lookpolymers.com/polymer_2085A-Polyurethane-based-Biomedical-Elastomer.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.32 g/cc	1.32 g/cc	ASTM D792

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	87	87	ASTM D2240
Tensile Strength, Ultimate	45.5 MPa	6600 psi	ASTM D412
Tensile Strength, Yield	5.52 MPa	800 psi	at 100%; ASTM D412
Elongation at Break	550 %	550 %	ASTM D412

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China