

3A Composites Core Materials AIREX® PXw.320 Fiber-Reinforced Structural Foam Panel

Category : Other Engineering Material , Composite Core Material , Polymer

Material Notes:

AIREX® PXw is a closed-cell, fiber reinforced polymer foam panel with a special formulation and very high mechanical properties. The sophisticated manufacturing process evenly distributes continuous glass fibers with woven fabrics throughout the foam. This generates a product with enhanced mechanical properties in flexure (bending), allowing it to be used with or without face sheets. AIREX® PXw is dimensionally stable, does not lose strength when wet, and is resistant to chemicals and high temperatures. It is ideally suited as a material for static applications requiring high stiffness or as a replacement for wood and plywood. Characteristics Stand alone product – does not need face sheets High flexural strength and stiffness Replacement for wood and plywood Good fastener pull-out strength High heat resistance Compatible with a wide range of resins and adhesives Dimensionally stable High styrene resistance Very low water absorption Non biodegradable Excellent chemical resistance Applications Marine: Floors, soles, bulkheads, transoms, stringers, engine beds, interiors, local reinforcements, tooling and molds Road and Rail: Floors, sidewalls, roofs, engine covers, interior panels Industrial: Covers, tanks, containers, floors, tooling and molds, concrete pouring forms, architectural panels, tub and shower enclosures

Order this product through the following link:

http://www.lookpolymers.com/polymer_3A-Composites-Core-Materials-AIREX-PXw320-Fiber-Reinforced-Structural-Foam-Panel.php

Physical Properties	Metric	English	Comments
Density	0.320 g/cc	0.0116 lb/in ³	apparent nominal; ASTM C271

Mechanical Properties	Metric	English	Comments
Flexural Strength	22.0 MPa @Thickness 19.0 mm	3190 psi @Thickness 0.750 in	ASTM D790
Flexural Modulus	1.87 GPa @Thickness 19.0 mm	271 ksi @Thickness 0.750 in	ASTM D790
Compressive Strength	1.50 MPa @Thickness 19.0 mm	218 psi @Thickness 0.750 in	perpendicular to plane; ASTM C365
Compressive Modulus	0.0720 GPa @Thickness 19.0 mm	10.4 ksi @Thickness 0.750 in	perpendicular to plane; ASTM C365
Shear Modulus	0.0440 GPa	6.38 ksi	ASTM C273
Shear Strength	0.900 MPa	131 psi	ASTM C273

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China