

3A Composites Core Materials BALTEK® SB.150 Structural End-Grain Balsa

Category : Other Engineering Material , Composite Core Material , Wood and Natural Products , Wood , Hardwood

Material Notes:

BALTEK® SB is a core material produced from certified kiln-dried balsa wood in the 'end-grain' configuration. It has extremely high strength and stiffness to weight ratios, and achieves an excellent bond with all types of resins and adhesives. It is compatible with a variety of manufacturing processes and is resistant to temperature changes, or exposure to fire, or chemicals such as styrene. BALTEK® SB is an ideal core material for an extensive range of applications. All while being a renewable resource.

Characteristics: Extremely high strength and stiffness to weight ratios
Excellent fire performance
Ecological product
Wide operating temperature range -212 °C to +163 °C (-414 °F to +325 °F)
Excellent fatigue resistance
Good sound and thermal insulation
High impact strength
Good moisture resistance

Applications
Marine: Hulls, decks, bulkheads, superstructures, interiors, tooling + molds
Road and Rail: Floors, walls, roof panels, body panels, interiors, front-ends, side skirts
Wind Energy: Rotor blades, spinners, nacelle covers, generator housings
Aircraft: Floor panels, galley carts, interior partitions, cargo pallets, containers, general aviation (sport aircraft) parts
Defense: Naval vessels, containers, cargo pallets, shelters
Industrial: Tooling, tanks, ductwork, impact limiter, concrete forms, fascia panels, skis, snowboards, wakeboards

Order this product through the following link:

http://www.lookpolymers.com/polymer_3A-Composites-Core-Materials-BALTEK-SB150-Structural-End-Grain-Balsa.php

Physical Properties	Metric	English	Comments
Density	0.247 g/cc	0.00892 lb/in ³	apparent nominal; ASTM C271

Mechanical Properties	Metric	English	Comments
Tensile Strength	23.5 MPa	3410 psi	perpendicular to plane; ASTM C297
Tensile Modulus	5.759 GPa	835.3 ksi	perpendicular to plane; ASTM C297
Compressive Strength	26.3 MPa	3810 psi	perpendicular to plane; ASTM C365
Compressive Modulus	7.982 GPa	1158 ksi	perpendicular to plane; ASTM C365
Shear Modulus	0.309 GPa	44.8 ksi	ASTM C273
Shear Strength	4.90 MPa	711 psi	ASTM C273

Thermal Properties	Metric	English	Comments
Thermal Conductivity	0.0840 W/m-K	0.583 BTU-in/hr-ft ² -°F	ASTM C177

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China