## 3M 4492W Double Coated Polyethylene Foam Tape

Category : Polymer , Adhesive

## Material Notes:

3M<sup>™</sup> Double Coated Polyethylene Foam Tapes 4462W, 4462B, 4466W and 4466B combine a conformable closed cell foam with a rubber adhesive that provides high initial adhesion to a variety of surfaces including polyethylene and polypropylene. 3M<sup>™</sup> Double Coated Polyethylene Foam Tapes 4492G, 4492W, 4492B, 4496W and 4496B combine a conformable closed cell foam with a high strength acrylic adhesive that provides good initial tack and offers high ultimate adhesion to a wide variety of surfaces.Information provided by 3M

## Order this product through the following link:

http://www.lookpolymers.com/polymer\_3M-4492W-Double-Coated-Polyethylene-Foam-Tape.php

| Physical Properties | Metric       | English        | Comments |
|---------------------|--------------|----------------|----------|
| Density             | 0.0960 g/cc  | 0.00347 lb/in³ |          |
| Thickness           | 20.3 microns | 0.800 mil      |          |

| Mechanical Properties     | Metric    | English  | Comments   |
|---------------------------|-----------|----------|--|
| Tensile Strength at Break | 0.415 MPa | 60.2 psi | Dynamic, 1 in. <sup>2</sup> (6.45<br>cm <sup>2</sup> ) overlap Jaw Speed<br>0.5 in./min (12.7 mm/min.); ASTM D-<br>897 |
| Peel Strength             | 1.40 kN/m | 8.00 pli | 90° Angle Peel 12 in./min. Jaw Speed<br>(308 mm/min.) 72 hour Dwell; ASTM<br>D3330                                     |

| Thermal Properties               | Metric  | English | Comments   |  |
|----------------------------------|---------|---------|------------|--|
| Maximum Service Temperature, Air | 70.0 °C | 158 °F  | Long Term  |  |
|                                  | 82.0 °C | 180 °F  | Short Term |  |

| Descriptive Properties | Value                                     | Comments |
|------------------------|---|----------|
| Adhesive Type          | 430                                       |          |
| Liner                  | Closed Cell Crosslinked Polyethylene Foam |          |

## Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com Email : sales@lookpolymers.com Tel : +86 021-51131842 Mobile : +86 13061808058 Skype : lookpolymers Address : United North Road 215,Fengxian District, Shanghai City,China