

## 3M 465 Adhesive Transfer Tape with 3M Adhesive 400

Category : Polymer , Adhesive

**Material Notes:**

3M™ Adhesive Transfer Tapes 463, 465, 9457 and 9665 with 3M™ Adhesive 400 are ideal for bonding together a wide variety of similar and dissimilar materials such as metals, glass, wood, papers, paints, and many plastics. Information provided by 3M

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_3M-465-Adhesive-Transfer-Tape-with-3M-Adhesive-400.php](http://www.lookpolymers.com/polymer_3M-465-Adhesive-Transfer-Tape-with-3M-Adhesive-400.php)

| Physical Properties | Metric       | English  | Comments      |
|---------------------|--------------|----------|---------------|
| Thickness           | 50.8 microns | 2.00 mil | Tape Only     |
|                     | 102 microns  | 4.00 mil | Release Liner |

| Mechanical Properties | Metric       | English    | Comments             |
|-----------------------|--------------|------------|----------------------|
| Peel Strength         | 0.27391 kN/m | 1.5625 pli | to Steel; ASTM D3330 |

| Thermal Properties               | Metric  | English | Comments   |
|----------------------------------|---------|---------|------------|
| Maximum Service Temperature, Air | 82.0 °C | 180 °F  | Long term  |
|                                  | 121 °C  | 250 °F  | Short term |

| Processing Properties | Metric     | English    | Comments |
|-----------------------|------------|------------|----------|
| Shelf Life            | 24.0 Month | 24.0 Month |          |

| Descriptive Properties | Value                          | Comments |
|------------------------|--------------------------------|----------|
| Liner                  | 60# Unbleached Densified Kraft |          |

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China