

3M 6035PC 12046 Polyurethane Foam Tape (20 lb./ft3 (320 kg/m3) Series)

Category: Polymer, Adhesive

Material Notes:

3M[™] series polyurethane foam substrates with a high performance, pressure-sensitive acrylic adhesive on one side. 3M[™] microcellular polyurethane foam is designed for high performance gasketing and sealing applications. Has excellent resistance to compression set and die cuts cleanly. 3M[™] acrylic adhesive provides an excellent bond to various surfaces and has good shear strength at elevated temperatures. Available in 15 lb/ft3 and 20 lb/ft3 densities.Information provided by 3M

Order this product through the following link:

http://www.lookpolymers.com/polymer_3M-6035PC-12046-Polyurethane-Foam-Tape-20-lbft3-320-kgm3-Series.php

| Physical Properties | Metric | English | Comments |
|---------------------|--------|---------|----------|
| Water Absorption | 4.0 % | 4.0 % | ASTMD570 |

| Mechanical Properties | Metric | English | Comments |
|-----------------------|------------|----------|-------------------------------|
| Elongation at Break | 100 % | 100 % | ASTMD3574-E Die E |
| Compressive Strength | 0.0552 MPa | 8.00 psi | Force Deflection; ASTMD3574-D |
| Tear Strength | 1.23 kN/m | 7.00 pli | |

| Thermal Properties | Metric | English | Comments |
|----------------------------------|----------|----------|----------|
| Maximum Service Temperature, Air | 107 °C | 225 °F | |
| Minimum Service Temperature, Air | -40.0 °C | -40.0 °F | |

| Processing Properties | Metric | English | Comments |
|-----------------------|------------|------------|----------|
| Shelf Life | 24.0 Month | 24.0 Month | |

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China