

3M 7680-S Cold Shrink QT-III Silicone Rubber Skirted Termination Kits

Category : Polymer , Thermoset , Silicone , Silicone Rubber

Material Notes:

3M™ Cold Shrink QT-III Silicone Rubber Skirted Termination Kits, 7620-S, 7680-S and 7690-S Series, contain one-piece, skirted, silicone Rubber Skirted Terminations, qualified as IEEE Standard 48 Class 1 for outdoor weather-exposed applications. The termination assemblies consist of a skirted insulator, high-dielectric constant (High-K) stress control tube, conformable High-K stress controlling compound and built-in environmental top sealing compound. The insulator is made of a dark gray silicone rubber with excellent tracking resistance and hydrophobic properties. Information provided by 3M

Order this product through the following link:

http://www.lookpolymers.com/polymer_3M-7680-S-Cold-Shrink-QT-III-Silicone-Rubber-Skirted-Termination-Kits.php

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	5.86 MPa	850 psi	Silicone Rubber Insulator; ASTM D412
	10.3 MPa	1490 psi	High-K Stress Control Tube; ASTM D412
100% Modulus	0.000896 GPa	0.130 ksi	Silicone Rubber Insulator; ASTM D412
	0.00110 GPa	0.160 ksi	High-K Stress Control Tube; ASTM D412
300% Modulus	0.00124 GPa	0.180 ksi	High-K Stress Control Tube; ASTM D412
	0.00276 GPa	0.400 ksi	Silicone Rubber Insulator; ASTM D412

Electrical Properties	Metric	English	Comments
Dielectric Constant	3.6	3.6	Silicone Rubber Insulator, 1000 V, 50% RH; ASTM D150
	@Frequency 60.0 Hz	@Frequency 60.0 Hz	
	22	22	High-K Stress Control Tube, 1000 V, 50% RH; ASTM D150
	@Frequency 60.0 Hz	@Frequency 60.0 Hz	
	25	25	High-K Stress Control Compound, 1000 V, 50% RH, 100 mil; ASTM D150
	@Frequency 60.0 Hz	@Frequency 60.0 Hz	
Dielectric Strength	11.8 kV/mm	300 kV/in	Environmental Sealing Compound; ASTM D149
	@Thickness 1.91 mm	@Thickness 0.0750 in	
	19.7 kV/mm	500 kV/in	Silicone Rubber Insulator; ASTM D149
	@Thickness 1.91 mm	@Thickness 0.0750 in	
	0.0030	0.0030	

Designation Factor Electrical Properties	Metric @Frequency 60.0 Hz	English @Frequency 60.0 Hz	Comments Silicone Rubber Insulator, 1000 V, 50% RH; ASTM D150
	0.10 @Frequency 60.0 Hz	0.10 @Frequency 60.0 Hz	High-K Stress Control Tube, 1000 V, 50% RH; ASTM D150
	0.90 @Thickness 2.54 mm, Frequency 60.0 Hz	0.90 @Thickness 0.100 in, Frequency 60.0 Hz	High-K Stress Control Compound, 1000 V, 50% RH; ASTM D150
Track Resistance	18000 sec	18000 sec	3.5 kV; ASTM 2303

Descriptive Properties	Value	Comments
Appearance	Dark Gray	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China