

3M 7735FL Acrylate Overlaminating Film

Category : Polymer , Adhesive

Material Notes:

3M™ Acrylate Overlaminating Film 7735FL utilizes an outdoor durable acrylate film facestock with exceptional UV resistance, combined with 3M™ Adhesive 400 and a film liner. This product offers excellent clarity and provides at least five years of outdoor life, when used with 3M™ Polyester Label Stocks, as explained below. Information provided by 3M

Order this product through the following link:

http://www.lookpolymers.com/polymer_3M-7735FL-Acrylate-Overlaminating-Film.php

Physical Properties	Metric	English	Comments
Thickness	20.3 microns	0.800 mil	Adhesive
	38.1 microns	1.50 mil	Liner
	76.2 microns	3.00 mil	Facestock

Mechanical Properties	Metric	English	Comments
Peel Strength	0.20817 kN/m	1.1875 pli	Polypropylene, 180° Peel, Initial 10 min dwell at RT; ASTM D3330
	0.20817 kN/m	1.1875 pli	Stainless Steel, 180° Peel, Conditioned for 3 days at RT; ASTM D3330
	0.27391 kN/m	1.5625 pli	Stainless Steel, 180° Peel, Initial 10 min dwell at RT; ASTM D3330

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	79.0 °C	174 °F	Service
Minimum Service Temperature, Air	-40.0 °C	-40.0 °F	Service
	-12.0 °C	10.4 °F	Application

Processing Properties	Metric	English	Comments
Shelf Life	24.0 Month	24.0 Month	

Descriptive Properties	Value	Comments
Adhesive Type	#400 Acrylic	
Liner	Clear Polyester Liner	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China