

## 3M 7840 Laser Toner Printable Polyester Label Material

Category : Polymer , Adhesive

### Material Notes:

3M™ Laser Toner Printable Polyester Label Materials 7840 and 7840TL are matte radiant white polyester label stocks that offer . These label products utilize 3M™ Adhesive 310 which is a firm adhesive which resists oozing and provides high strength on a variety of surfaces including high surface energy (HSE) plastics and metals. Information provided by 3M

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_3M-7840-Laser-Toner-Printable-Polyester-Label-Material.php](http://www.lookpolymers.com/polymer_3M-7840-Laser-Toner-Printable-Polyester-Label-Material.php)

Physical Properties	Metric	English	Comments
Thickness	20.3 microns	0.800 mil	Adhesive
	58.4 microns	2.30 mil	Facestock, Matte radiant white polyester
	81.3 microns	3.20 mil	Liner

Mechanical Properties	Metric	English	Comments
Peel Strength	0.05478 kN/m	0.3125 pli	LD Polyethylene, 180° Peel, Conditioned for 3 days at 49°C; ASTM D3330
	0.0877 kN/m	0.500 pli	LD Polyethylene, 90° Peel, Conditioned for 3 days at 49°C; ASTM D3330
	0.131 kN/m	0.750 pli	LD Polyethylene, 90° Peel, Initial, 10 min dwell at RT; ASTM D3330
	0.175 kN/m	1.00 pli	Polypropylene, 90° Peel, Initial, 10 min dwell at RT; ASTM D3330
	0.175 kN/m	1.00 pli	HD Polyethylene, 90° Peel, Initial, 10 min dwell at RT; ASTM D3330
	0.1972 kN/m	1.125 pli	Polypropylene, 180° Peel, Initial, 10 min dwell at RT; ASTM D3330
	0.1972 kN/m	1.125 pli	Polypropylene, 180° Peel, Conditioned for 3 days at RT; ASTM D3330
	0.219 kN/m	1.25 pli	LD Polyethylene, 180° Peel, Initial, 10 min dwell at RT; ASTM D3330
	0.219 kN/m	1.25 pli	HD Polyethylene, 90° Peel, Conditioned for 3 days at RT; ASTM D3330
	0.219 kN/m	1.25 pli	HD Polyethylene, 90° Peel, Conditioned for 3 days at 49°C; ASTM D3330
	0.219 kN/m	1.25 pli	LD Polyethylene, 180° Peel, Conditioned for 24 hrs at 32°C at 90%

Mechanical Properties	Metric	English	RH: ASTM D3330 Comments
	0.2410 kN/m	1.375 pli	LD Polyethylene, 90° Peel, Conditioned for 3 days at RT; ASTM D3330
	0.263 kN/m	1.50 pli	HD Polyethylene, 180° Peel, Initial, 10 min dwell at RT; ASTM D3330
	0.263 kN/m	1.50 pli	Polypropylene, 90° Peel, Conditioned for 3 days at RT; ASTM D3330
	0.263 kN/m	1.50 pli	LD Polyethylene, 90° Peel, Conditioned for 24 hrs at 32°C at 90% RH; ASTM D3330
	0.29582 kN/m	1.6875 pli	Polypropylene, 90° Peel, Conditioned for 24 hrs at 32°C at 90% RH; ASTM D3330
	0.29582 kN/m	1.6875 pli	HD Polyethylene, 90° Peel, Conditioned for 24 hrs at 32°C at 90% RH; ASTM D3330
	0.3287 kN/m	1.875 pli	HD Polyethylene, 180° Peel, Conditioned for 3 days at 49°C; ASTM D3330
	0.3287 kN/m	1.875 pli	Polypropylene, 90° Peel, Conditioned for 3 days at 49°C; ASTM D3330
	0.351 kN/m	2.00 pli	LD Polyethylene, 180° Peel, Conditioned for 3 days at RT; ASTM D3330
	0.351 kN/m	2.00 pli	Polycarbonate 90° Peel, Conditioned for 3 days at 49°C; ASTM D3330
	0.351 kN/m	2.00 pli	Glass, 90° Peel, Conditioned for 24 hrs at 32°C at 90% RH; ASTM D3330
	0.36156 kN/m	2.0625 pli	HD Polyethylene, 180° Peel, Conditioned for 3 days at RT; ASTM D3330
	0.3725 kN/m	2.125 pli	Glass, 90° Peel, Initial, 10 min dwell at RT; ASTM D3330
	0.38347 kN/m	2.1875 pli	Stainless Steel, 90° Peel, Initial, 10 min dwell at RT; ASTM D3330
	0.38347 kN/m	2.1875 pli	Polypropylene, 180° Peel, Conditioned for 3 days at 49°C; ASTM D3330
	0.38347 kN/m	2.1875 pli	HD Polyethylene, 180° Peel, Conditioned for 24 hrs at 32°C at 90% RH; ASTM D3330
	0.40538 kN/m	2.3125 pli	Polycarbonate 90° Peel, Initial, 10 min dwell at RT; ASTM D3330
	0.4163 kN/m	2.375 pli	Polypropylene, 180° Peel, Conditioned for 24 hrs at 32°C at 90% RH; ASTM D3330

Mechanical Properties	Metric	English	Comments
			Polycarbonate 90° Peel, Conditioned for 3 days at 32°C at 90% RH; ASTM D3330
	0.44921 kN/m	2.5625 pli	Stainless Steel, 90° Peel, Conditioned for 3 days at RT; ASTM D3330
	0.44921 kN/m	2.5625 pli	Polycarbonate 180° Peel, Conditioned for 3 days at 49°C; ASTM D3330
	0.4602 kN/m	2.625 pli	Glass, 90° Peel, Conditioned for 3 days at 49°C; ASTM D3330
	0.47112 kN/m	2.6875 pli	Stainless Steel, 180° Peel, Initial, 10 min dwell at RT; ASTM D3330
	0.47112 kN/m	2.6875 pli	Polycarbonate 90° Peel, Conditioned for 3 days at RT; ASTM D3330
	0.5040 kN/m	2.875 pli	Stainless Steel, 90° Peel, Conditioned for 3 days at 49°C; ASTM D3330
	0.5040 kN/m	2.875 pli	Stainless Steel, 90° Peel, Conditioned for 24 hrs at 32°C at 90% RH; ASTM D3330
	0.51494 kN/m	2.9375 pli	Polycarbonate 180° Peel, Initial, 10 min dwell at RT; ASTM D3330
	0.51494 kN/m	2.9375 pli	Glass, 90° Peel, Conditioned for 3 days at RT; ASTM D3330
	0.55877 kN/m	3.1875 pli	Stainless Steel, 180° Peel, Conditioned for 3 days at RT; ASTM D3330
	0.570 kN/m	3.25 pli	Glass, 180° Peel, Initial, 10 min dwell at RT; ASTM D3330
	0.570 kN/m	3.25 pli	Polycarbonate 180° Peel, Conditioned for 3 days at RT; ASTM D3330
	0.657 kN/m	3.75 pli	Stainless Steel, 180° Peel, Conditioned for 3 days at 49°C; ASTM D3330
	0.6793 kN/m	3.875 pli	Polycarbonate 180° Peel, Conditioned for 24 hrs at 32°C at 90% RH; ASTM D3330
	0.7231 kN/m	4.125 pli	Glass, 180° Peel, Conditioned for 24 hrs at 32°C at 90% RH; ASTM D3330
	0.745 kN/m	4.25 pli	Glass, 180° Peel, Conditioned for 3 days at RT; ASTM D3330
	0.745 kN/m	4.25 pli	Glass, 180° Peel, Conditioned for 3 days at 49°C; ASTM D3330
	0.8108 kN/m	4.625 pli	Stainless Steel, 180° Peel, Conditioned for 24 hrs at 32°C at 90% RH; ASTM D3330

Processing Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Processing Properties	Metric <sup>cnth</sup>	English <sup>nth</sup>	Comments
Descriptive Properties		Value	Comments
Adhesive Type		#310 Acrylic	
Liner		55# Densified kraft	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China