

3M 8420-6 Cold Shrink Connector Insulators

Category: Polymer, Thermoset, Rubber or Thermoset Elastomer (TSE)

Material Notes:

3M™ Cold Shrink Connector Insulators are open-ended, tubular, rubber sleeves which are factory expanded and assembled onto a removable core. The core is removed after the tube has been positioned for installation over an inline connection, terminal lug, etc, allowing the tube to shrink and form a water-resistant seal. The insulating tube is made of EPDM rubber which contains no chlorides or sulfur. Six diameter sizes will cover a range of cable up to 1000 volts for copper and aluminum conductors from 10 AWG through 1000 kcmil.Information provided by 3M

Order this product through the following link:

http://www.lookpolymers.com/polymer_3M-8420-6-Cold-Shrink-Connector-Insulators.php

| Mechanical Properties | Metric | English | Comments |
|----------------------------|--------------|-----------|----------------------|
| Tensile Strength, Ultimate | 9.65 MPa | 1400 psi | ASTM D412-75 |
| Elongation at Break | 750 % | 750 % | ASTM D412-75 |
| 300% Modulus | 0.00331 GPa | 0.480 ksi | ASTM D412-75 |
| Tear Strength | 26.3 kN/m | 150 pli | Die C; ASTM D624C-73 |

| Electrical Properties | Metric | English | Comments |
|-----------------------|--------------------|----------------------|--|
| Dielectric Strength | 11.1 kV/mm | 282 kV/in | 7 days @ 90°C in water; ASTM D149- 75 |
| | 14.4 kV/mm | 365 kV/in | Original; ASTM D149-75 |
| | @Thickness 1.78 mm | @Thickness 0.0700 in | |

| Processing Properties | Metric | English | Comments |
|-----------------------|--------|---------|------------------------|
| Moisture Content | 1.8 % | 1.8 % | 7 days @ 90°C in water |

| Descriptive Properties | Value | Comments |
|------------------------|-------|----------|
| Appearance | Black | |

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China

