

## 3M 9627 Adhesive Transfer Tape with Quick Bonding Adhesive 360

Category : Polymer , Adhesive

**Material Notes:**

3M™ Adhesive Transfer Tapes with 3M™ Quick Bonding Adhesive 360 provides high bond strength to most surfaces, including many low surface energy plastics such as polypropylene and powder coated paints. Information provided by 3M

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_3M-9627-Adhesive-Transfer-Tape-with-Quick-Bonding-Adhesive-360.php](http://www.lookpolymers.com/polymer_3M-9627-Adhesive-Transfer-Tape-with-Quick-Bonding-Adhesive-360.php)

Physical Properties	Metric	English	Comments
Thickness	81.3 microns	3.20 mil	Liner
	127 microns	5.00 mil	Adhesive

Mechanical Properties	Metric	English	Comments
Peel Strength	0.877 kN/m	5.00 pli	HDPE, 180°, 2 mil al foil, 72 hr RT, Faceside; ASTM D3330
	0.877 kN/m	5.00 pli	HDPE, 180°, 2 mil al foil, 72 hr RT, Backside; ASTM D3330
	0.9861 kN/m	5.625 pli	LDPE, 180°, 2 mil al foil, 72 hr RT, Backside; ASTM D3330
	1.0408 kN/m	5.9375 pli	LDPE, 180°, 2 mil al foil, 72 hr RT, Faceside; ASTM D3330
	1.643 kN/m	9.375 pli	Polypropylene, 180°, 2 mil al foil, 30 sec RT, Backside; ASTM D3330
	1.6982 kN/m	9.6875 pli	Polypropylene, 180°, 2 mil al foil, 30 sec RT, Backside; ASTM D3330
	1.75 kN/m	10.0 pli	Polypropylene, 180°, 2 mil al foil, 30 sec RT, Faceside; ASTM D3330
	1.75 kN/m	10.0 pli	Stainless Steel, 180°, 2 mil al foil, 72 hr RT, Backside; ASTM D3330
	1.808 kN/m	10.31 pli	Polycarbonate, 180°, 2 mil al foil, 72 hr RT, Faceside; ASTM D3330
	1.808 kN/m	10.31 pli	Polycarbonate, 180°, 2 mil al foil, 72 hr RT, Backside; ASTM D3330
	1.808 kN/m	10.31 pli	Polypropylene, 180°, 2 mil al foil, 30 sec RT, Faceside; ASTM D3330
	1.808 kN/m	10.31 pli	Polypropylene, 180°, 2 mil al foil, 72 hr RT, Faceside; ASTM D3330
	1.808 kN/m	10.31 pli	Polypropylene, 180°, 2 mil al foil, 72 hr RT, Backside; ASTM D3330
1.808 kN/m	10.31 pli	ABS, 180°, 2 mil al foil, 72 hr RT,	

Mechanical Properties	Metric	English	Faceside: ASTM D3330 Comments
	1.808 kN/m	10.31 pli	ABS, 180°, 2 mil al foil, 72 hr RT, Backside; ASTM D3330
	1.808 kN/m	10.31 pli	Stainless Steel, 180°, 2 mil al foil, 72 hr RT, Faceside; ASTM D3330

Processing Properties	Metric	English	Comments
Shelf Life	24.0 Month	24.0 Month	

Descriptive Properties	Value	Comments
Liner	Natural, 60#	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China