

## 3M 9675 Adhesive Transfer Tapes with Adhesive 350

Category : Polymer , Adhesive

### Material Notes:

These 3M™ Adhesive Transfer Tapes with 3M™ Adhesive 350 are a modified acrylic adhesive ideal for very high-bond strength to many surfaces. They have excellent chemical resistance and bold strength even at elevated temperatures. These tapes are offered with a fiber reinforced adhesive which is important for roll stability in narrow widths. Tapes using adhesive 350 are designed for temperature exposure to 450°F (232°C) for short periods of time and up to 300°F (149°C) over long time frames. This adhesive is a good choice for applications which require adhesion to Low Surface Energy plastics, powder coatings and oily metals. Information provided by 3M

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_3M-9675-Adhesive-Transfer-Tapes-with-Adhesive-350.php](http://www.lookpolymers.com/polymer_3M-9675-Adhesive-Transfer-Tapes-with-Adhesive-350.php)

Physical Properties	Metric	English	Comments
Thickness	127 microns	5.00 mil	

Mechanical Properties	Metric	English	Comments
Peel Strength	0.38347 kN/m	2.1875 pli	H.D. Polyethylene, 180° peel, 72°F, (72 hr. dwell); ASTM D3330
	0.438 kN/m	2.50 pli	L.D. Polyethylene, 180° peel, 72°F, (72 hr. dwell); ASTM D3330
	0.877 kN/m	5.00 pli	Polypropylene, 180° peel, 72°F, (72 hr. dwell); ASTM D3330
	0.93128 kN/m	5.3125 pli	ABS, 180° peel, 72°F, (72 hr. dwell); ASTM D3330
	0.9861 kN/m	5.625 pli	Rigid PVC, 180° peel, 72°F, (72 hr. dwell); ASTM D3330
	1.05 kN/m	6.00 pli	Aluminum, 180° peel, 72°F, (72 hr. dwell); ASTM D3330
	1.31 kN/m	7.50 pli	Epoxy, 180° peel, 72°F, (72 hr. dwell); ASTM D3330
	1.3695 kN/m	7.8125 pli	Acrylic, 180° peel, 72°F, (72 hr. dwell); ASTM D3330
	1.5887 kN/m	9.0625 pli	Painted Metal, 180° peel, 72°F, (72 hr. dwell); ASTM D3330
	1.5887 kN/m	9.0625 pli	Glass, 180° peel, 72°F, (72 hr. dwell); ASTM D3330
1.5887 kN/m	9.0625 pli	Polycarbonate, 180° peel, 72°F, (72 hr. dwell); ASTM D3330	
1.643 kN/m	9.375 pli	Stainless Steel, 180° peel, 72°F, (72 hr. dwell); ASTM D3330	

Thermal Properties	Metric	English	Comments
Minimum Service Temperature, Air	-40.0 °C	-40.0 °F	

Processing Properties	Metric	English	Comments
Shelf Life	24.0 Month	24.0 Month	

Descriptive Properties	Value	Comments
Liner	83# Polycoated Kraft lay flat - 6.2 mils thick	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China