

3M Controltac™ IJ3552C Changeable Graphic Film with Comply™ Adhesive

Category : Polymer , Film

Material Notes:

2-mil white, vinyl film; Pressure-activated adhesive for easy sliding, tacking, snap up and repositioning; Conforms to surface with corrugations and rivets; Air release channels for fast, easy, bubble-free installations and Removable without heat or chemicals Information provided by 3M

Order this product through the following link:

http://www.lookpolymers.com/polymer_3M-Controltac-IJ3552C-Changeable-Graphic-Film-with-Comply-Adhesive.php

| Physical Properties | Metric | English | Comments |
|---------------------|--------------------|-----------------|------------------|
| Thickness | 50.8 microns | 2.00 mil | without adhesive |
| | 76.2 - 102 microns | 3.00 - 4.00 mil | with adhesive |

| Mechanical Properties | Metric | English | Comments |
|---------------------------|-------------|-------------|---|
| Tensile Strength at Break | >= 17.2 MPa | >= 2490 psi | |
| Peel Strength | 0.105 kN/m | 0.600 pli | Adhesion to Glass |
| | 0.298 kN/m | 1.70 pli | Adhesion to Fruehauf pre-painted panels |
| | 0.666 kN/m | 3.80 pli | Adhesion to ABS |

| Thermal Properties | Metric | English | Comments |
|----------------------------------|---------|---------|---------------------------------------|
| Maximum Service Temperature, Air | 38.0 °C | 100 °F | Flat surfaces with and without rivets |
| | 38.0 °C | 100 °F | Cured surfaces |
| Minimum Service Temperature, Air | 2.00 °C | 35.6 °F | Flat surfaces with and without rivets |
| | 15.0 °C | 59.0 °F | Cured surfaces |

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China