

## 3M Cushion-Mount™ E1060H Plus Plate Mounting Tapes with Easy Mount Adhesive and High Plateside Adhesion

Category : Polymer , Adhesive

### Material Notes:

3M™ Cushion-Mount™ Plus Plate Mounting Tapes with Easy Mount Adhesive and High Plateside Adhesion are designed for mounting flexographic print plates to cylinders or sleeves. This family of foam mounting tapes provides excellent print quality for combination printing, process printing, solids and line work. 3M now offers a range of 40 and 60 mil cushioned plate mounting tapes for flexographic printing needs. Information provided by 3M

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_3M-Cushion-Mount-E1060H-Plus-Plate-Mounting-Tapes-with-Easy-Mount-Adhesive-and-High-Plateside-Adhesion.php](http://www.lookpolymers.com/polymer_3M-Cushion-Mount-E1060H-Plus-Plate-Mounting-Tapes-with-Easy-Mount-Adhesive-and-High-Plateside-Adhesion.php)

Physical Properties	Metric	English	Comments
Density	0.450 g/cc	0.0163 lb/in <sup>3</sup>	
Thickness	114 microns	4.50 mil	Film Liner
	1570 microns	62.0 mil	Tape

Mechanical Properties	Metric	English	Comments
Compressive Strength	0.103 MPa	15.0 psi	10% Compression, Deflection
	0.172 MPa	25.0 psi	25% Compression, Deflection
Peel Strength	0.38347 kN/m	2.1875 pli	Linered side-Photopolymer, Adhesion; ASTM D3330
	0.5478 kN/m	3.125 pli	Non-linered side-Composite Sleeve, Adhesion; ASTM D3330
	0.60259 kN/m	3.4375 pli	Non-linered side-Urethane-B, Adhesion; ASTM D3330
	0.657 kN/m	3.75 pli	Non-linered side-Stainless Steel, Adhesion; ASTM D3330
	0.71216 kN/m	4.0625 pli	Non-linered side-Polyester, Adhesion; ASTM D3330
	0.7669 kN/m	4.375 pli	Non-linered side-Urethane-A, Adhesion; ASTM D3330

Descriptive Properties	Value	Comments
Liner	Standard White Foam	

Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China