

3M Dyneon™ Aflas® FA-150P PTFE Fluoroelastomer (discontinued **)

Category : Polymer , Thermoset , Fluoropolymer, TS , Thermoset Fluoroelastomer , Rubber or Thermoset Elastomer (TSE)

Material Notes:

Data provided by the manufacturer, Dyneon LLC. Non-incorporated cure polymer, 57%F in polymer with 19% Medium Thermal Carbon Black (N990), 4% Triallyl Isocyanurate (TAIC), 1% Percadox™ 14, 1% Sodium Stearate. General purpose grade for calendaring, molding and extrusions. Used in Aggressive Oil/Coolant/Base Resistant Applications.

Order this product through the following link:

http://www.lookpolymers.com/polymer_3M-Dyneon-Aflas-FA-150P-PTFE-Fluoroelastomer-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	1.55 g/cc	0.0560 lb/in ³	
Oxygen Transmission	150 cc-mm/m ² -24hr-atm	381 cc-mil/100 in ² -24hr-atm	
Mooney Viscosity	95 @Temperature 100 °C	95 @Temperature 212 °F	ML1+10

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	71	71	
Tensile Strength, Ultimate	16.0 MPa	2320 psi	
Tensile Strength, Yield	3.00 MPa	435 psi	M100
Elongation at Break	350 %	350 %	
Coefficient of Friction, Dynamic	0.70	0.70	
Compression Set	44 % @Temperature 200 °C	44 % @Temperature 392 °F	70 hr; ASTM D395B

Thermal Properties	Metric	English	Comments
CTE, linear	240 μm/m-°C @Temperature 20.0 °C	133 μin/in-°F @Temperature 68.0 °F	
Specific Heat Capacity	1.67 J/g-°C	0.399 BTU/lb-°F	
Thermal Conductivity	0.200 W/m-K	1.39 BTU-in/hr-ft ² -°F	
Glass Transition Temp, Tg	2.00 °C	35.6 °F	TR10

Electrical Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Electrical Properties	Metric 1.00e+15 - 1.00e+16 GPa/cm	English 1.00e+15 - 1.00e+16 GPa/cm	Comments
Dielectric Constant	2.5 @Frequency 6.00e+7 Hz	2.5 @Frequency 6.00e+7 Hz	
Dielectric Strength	23.0 kV/mm	584 kV/in	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China