

## **3M Dyneon™ CC105 Custom Fluoropolymer Compound (discontinued \*\*)**

Category: Polymer, Thermoplastic, Fluoropolymer

**Material Notes:** 

This compound consists of a mixture of 25% fiberglass blended with PTFEInformation provided by Dyneon, A 3M Company

Order this product through the following link:

http://www.lookpolymers.com/polymer\_3M-Dyneon-CC105-Custom-Fluoropolymer-Compound-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Specific Gravity	2.15 g/cc	2.15 g/cc	ASTM D4745
Bulk Density	0.580 g/cc	0.0210 lb/in³	ASTM D4745

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	17.2 MPa	2500 psi	ASTM D4745
Elongation at Break	230 %	230 %	ASTM D4645

## **Contact Songhan Plastic Technology Co.,Ltd.**

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China