

3M Dyneon™ CC174/N Custom Fluoropolymer Compound (discontinued **)

Category : Polymer , Thermoplastic , Fluoropolymer

Material Notes:

This compound consists of a mixture of 15% fiberglass & 5% natural molybdenum disulfide blended with PTFE. Information provided by Dyneon, A 3M Company

Order this product through the following link:

http://www.lookpolymers.com/polymer_3M-Dyneon-CC174N-Custom-Fluoropolymer-Compound-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Specific Gravity	2.27 g/cc	2.27 g/cc	ASTM D4745
Bulk Density	0.520 g/cc	0.0188 lb/in ³	ASTM D4745

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	23.4 MPa	3400 psi	ASTM D4745
Elongation at Break	240 %	240 %	ASTM D4645

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China