

3M Dyneon™ CC605 PTFE 25% Fiberglass Filled (discontinued **)

Category : Polymer , Thermoplastic , Fluoropolymer , PTFE , Polytetrafluoroethylene (PTFE), Glass Filled, Molded

Material Notes:

Product Form: White, pelletized free-flowing powder. Applications include bearings, valve seats, seals. Data provided by Dyneon.

Order this product through the following link:

http://www.lookpolymers.com/polymer_3M-Dyneon-CC605-PTFE-25-Fiberglass-Filled-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Bulk Density	0.730 g/cc	0.0264 lb/in ³	ASTM D4894
Density	2.22 g/cc	0.0802 lb/in ³	ASTM D4894
Particle Size	750 µm	750 µm	ASTM D4894
Deformation	3.0 %	3.0 %	ASTM D621
	@Pressure 15.00 MPa	@Pressure 2175 psi	
	7.0 %	7.0 %	ASTM D621
	@Time 86400 sec, Pressure 15.00 MPa	@Time 24.0 hour, Pressure 2175 psi	

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	57	57	value after 15 sec; ASTM D2240
	62	62	initial value; ASTM D2240
Tensile Strength at Break	17.2 MPa	2490 psi	ASTM D4894
Elongation at Break	230 %	230 %	ASTM D4894
Tensile Modulus	0.159 GPa	23.0 ksi	ASTM D638

Thermal Properties	Metric	English	Comments
CTE, linear	50.0 µm/m-°C	27.8 µin/in-°F	ASTM E831
	@Temperature 30.0 - 100 °C	@Temperature 86.0 - 212 °F	
	122 µm/m-°C	68.0 µin/in-°F	ASTM E831
	@Temperature 100 - 200 °C	@Temperature 212 - 392 °F	
	151 µm/m-°C	84.0 µin/in-°F	ASTM E831
	@Temperature 200 - 300 °C	@Temperature 392 - 572 °F	

Thermal Properties	0.290 W/m-K Metric	2.01 BTU-in/hr-ft ² -°F English	Comments
	@Temperature 100 °C	@Temperature 212 °F	
	0.300 W/m-K	2.08 BTU-in/hr-ft ² -°F	ASTM E1530
	@Temperature 250 °C	@Temperature 482 °F	
Shrinkage	1.6 %	1.6 %	ASTM D4894

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China