

## 3M Dyneon™ FC 2179 Fluoroelastomer

Category : Polymer , Thermoset , Fluoropolymer, TS , Rubber or Thermoset Elastomer (TSE)

### Material Notes:

3M™ Dyneon™ Fluoroelastomer FC 2179 can be compounded using standard water cooled internal mixers or two-roll mills with standard fillers and ingredients utilized in typical fluoroelastomer formulations. The “dry” ingredients should be blended before adding to the masticated gum. For best results, Dyneon FC 2179 should be banded on the mill several minutes prior to adding the blended dry ingredients. Once mixed, the compounded stocks have good scorch resistance and storage stability. Composition: di-polymer of vinylidene fluoride and hexafluoropropylene High viscosity Process targets: compression molding Excellent compression set resistance Proprietary incorporated cure technology Information provided by Dyneon, A 3M Company

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_3M-Dyneon-FC-2179-Fluoroelastomer.php](http://www.lookpolymers.com/polymer_3M-Dyneon-FC-2179-Fluoroelastomer.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.80 g/cc	1.80 g/cc	
Mooney Viscosity	80 @Temperature 121 °C	80 @Temperature 250 °F	ML1+10

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	76	76	Press Cure 5 minutes @ 177°C, Post Cure 24 hours @ 260°C; ASTM D2240
Tensile Strength at Break	17.06 MPa	2475 psi	Press Cure 5 minutes @ 177°C, Post Cure 24 hours @ 260°C
Elongation at Break	180 %	180 %	Press Cure 5 minutes @ 177°C, Post Cure 24 hours @ 260°C
100% Modulus	0.00758 GPa	1.10 ksi	Press Cure 5 minutes @ 177°C, Post Cure 24 hours @ 260°C
Compression Set	10 %	10 %	Aged 70 hours @ 200°C, -214 O-rings; ASTM D395 Method B

Thermal Properties	Metric	English	Comments
Transformation Temperature	-18.0 °C	-0.400 °F	TR10; ASTM D1329

Component Elements Properties	Metric	English	Comments
Fluorine, F	65.9 %	65.9 %	

Descriptive Properties	Value	Comments
Color	Opaque Off-White	
MH, Maximum Torque		100 cpm, 0.5° Arc, 6 Minutes @ 177°C

Descriptive Properties	27.8 inch-lb Value	Comments
ML, Minimum Torque	3.6 inch-lb	100 cpm, 0.5° Arc, 6 Minutes @ 177°C
Solubility	Ketones and Esters	
t <sup>50</sup> , Time to 50% cure	1.9 minutes	100 cpm, 0.5° Arc, 6 Minutes @ 177°C
t <sup>90</sup> - Time to 90% cure	2.5 minutes	100 cpm, 0.5° Arc, 6 Minutes @ 177°C
ts2 - Time to 2 in-lb rise from min	1.3 minutes	100 cpm, 0.5° Arc, 6 Minutes @ 177°C

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China