

## 3M Dyneon™ Fluorel™ FC-2179 Fluoroelastomer VF2 + HFP Dipolymer (discontinued \*\*)

Category : Polymer , Thermoset , Fluoropolymer, TS , Thermoset Fluoroelastomer , Rubber or Thermoset Elastomer (TSE)

### Material Notes:

Data provided by the manufacturer, Dyneon LLC. Incorporated cure polymer, 65.9%F in polymer with 22% Medium Thermal Carbon Black (N990), 2% MgO, and 4% Ca(OH)<sub>2</sub>. Excellent processability. Suggested alternative: FE-5660Q. Used in O-Ring Applications.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_3M-Dyneon-Fluorel-FC-2179-Fluoroelastomer-VF2-HFP-Dipolymer-nbspdiscontinued-.php](http://www.lookpolymers.com/polymer_3M-Dyneon-Fluorel-FC-2179-Fluoroelastomer-VF2-HFP-Dipolymer-nbspdiscontinued-.php)

Physical Properties	Metric	English	Comments
Density	1.80 g/cc	0.0650 lb/in <sup>3</sup>	
Oxygen Transmission	98.0 cc-mm/m <sup>2</sup> -24hr-atm	249 cc-mil/100 in <sup>2</sup> -24hr-atm	
Mooney Viscosity	80 @Temperature 121 °C	80 @Temperature 250 °F	ML1+10

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	76	76	
Tensile Strength, Ultimate	17.0 MPa	2470 psi	
Tensile Strength, Yield	7.60 MPa	1100 psi	M100
Elongation at Break	180 %	180 %	
Coefficient of Friction, Dynamic	0.80	0.80	
Compression Set	10 % @Temperature 200 °C	10 % @Temperature 392 °F	70 hr; ASTM D395B

Thermal Properties	Metric	English	Comments
CTE, linear	200 μm/m-°C @Temperature 20.0 °C	111 μin/in-°F @Temperature 68.0 °F	
Specific Heat Capacity	1.65 J/g-°C	0.394 BTU/lb-°F	
Thermal Conductivity	0.240 W/m-K	1.67 BTU-in/hr-ft <sup>2</sup> -°F	
Glass Transition Temp, Tg	-18.0 °C	-0.400 °F	TR10

Electrical Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Electrical Properties	Metric 1.00e+13 - 1.00e+14 0.001 Cm	English 1.00e+13 - 1.00e+14 0.001 Cm	Comments
Dielectric Constant	11.4 @Frequency 6.00e+7 Hz	11.4 @Frequency 6.00e+7 Hz	
Dielectric Strength	25.0 kV/mm	635 kV/in	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China