

3M Dyneon™ PFA 6502N Perfluoroalkoxy Fluorothermoplastic (discontinued **)

Category : Polymer , Thermoplastic , Fluoropolymer , PFA

Material Notes:

The excellent chemical temperature resistance of Dyneon™ 6500N PFA is available across a range of melt flow indices, for optimal processability. Dyneon™ PFA 6502N, the highest molecular weight grade (lowest MFI) offers maximum stress crack resistance and tensile strength. It is ideal for applications such as tubing and sheeting. Dyneon™ PFA 6515 and PFA 6525N are designed for higher speed or higher shear processing such as injection molding and wire insulation. Dyneon PFA 6500 series products achieve the excellent property balance for which PFA is known including wide service temperature range (-200° to +260°C), almost universal chemical and solvent resistance, outstanding mechanical properties, resistance to weathering, low friction/non-stick behavior, high dielectric strength, and flame resistance. Information provided by Dyneon, A 3M Company

Order this product through the following link:

http://www.lookpolymers.com/polymer_3M-Dyneon-PFA-6502N-Perfluoroalkoxy-Fluorothermoplastic-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Specific Gravity	2.15 g/cc	2.15 g/cc	ASTM D792
Melt Index of Compound	2.0 g/10 min	2.0 g/10 min	ASTM D1238
	@Load 5.00 kg, Temperature 372 °C	@Load 11.0 lb, Temperature 702 °F	

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	60	60	ASTM D2240
Tensile Strength at Break	34.0 MPa	4930 psi	ASTM D638
Elongation at Break	400 %	400 %	ASTM D638
Flexural Modulus	0.550 GPa	79.8 ksi	ASTM D790

Thermal Properties	Metric	English	Comments
Melting Point	310 °C	590 °F	ASTM D4591
Flammability, UL94	V-0	V-0	
Oxygen Index	>= 95 %	>= 95 %	ASTM D2863

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China