3M Dyneon[™] PFA 6505N Perfluoroalkoxy Fluorothermoplastic (discontinued **)

Category : Polymer , Thermoplastic , Fluoropolymer , PFA

Material Notes:

The excellent chemical temperature resistance of Dyneon[™] 6500N PFA is available across a range of melt flow indices, for optimal processability. Dyneon[™] PFA 6502N, the highest molecular weight grade (lowest MFI) offers maximum stress crack resistance and tensile strength. It is ideal for applications such as tubing and sheeting. Dyneon[™] PFA 6515 and PFA 6525N are designed for higher speed or higher shear processing such as injection molding and wire insulation. Dyneon PFA 6500 series products achieve the excellent property balance for which PFA is known including wide service temperature range (-200° to +260°C), almost universal chemical and solvent resistance, outstanding mechanical properties, resistance to weathering, low friction/non-stick behavior, high dielectric strength, and flame resistance.Information provided by Dyneon, A 3M Company

Order this product through the following link:

http://www.lookpolymers.com/polymer_3M-Dyneon-PFA-6505N-Perfluoroalkoxy-Fluorothermoplastic-nbspdiscontinued-.php

| Physical Properties | Metric | English | Comments |
|------------------------|--------------------------------------|--------------------------------------|------------|
| Specific Gravity | 2.15 g/cc | 2.15 g/cc | ASTM D792 |
| Melt Index of Compound | 5.0 g/10 min | 5.0 g/10 min | ASTM D1238 |
| | @Load 5.00 kg, Temperature 372 °C | @Load 11.0 lb, Temperature 702 °F | |

| Mechanical Properties | Metric | English | Comments |
|---------------------------|-----------|----------|------------|
| Hardness, Shore D | 60 | 60 | ASTM D2240 |
| Tensile Strength at Break | 32.0 MPa | 4640 psi | ASTM D638 |
| Elongation at Break | 410 % | 410 % | ASTM D638 |
| Flexural Modulus | 0.550 GPa | 79.8 ksi | ASTM D790 |

| Thermal Properties | Metric | English | Comments |
|--------------------|---------|---------|------------|
| Melting Point | 308 °C | 586 °F | ASTM D4591 |
| Flammability, UL94 | V-0 | V-0 | |
| Oxygen Index | >= 95 % | >= 95 % | ASTM D2863 |

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com Email : sales@lookpolymers.com Tel : +86 021-51131842 Mobile : +86 13061808058



Skype : lookpolymers Address : United North Road 215, Fengxian District, Shanghai City, China