

3M Dyneon™ PFA 6515 UHPZ Perfluoroalkoxy Fluorothermoplastic Granules

Category : Polymer , Thermoplastic , Fluoropolymer , PFA

Material Notes:

Dyneon PFA X 6502 UPH, PFA X 6505 UHP and PFA X 6515 UHP are a new series of ultra-high purity fluorothermoplastics. These resins were developed for high-purity applications requiring ultra-low levels of metal and ion extraction, such as in the semiconductor market. The Dyneon PFA UHP family comprises grades that can be extruded, injection-molded, compression-molded, transfer-molded, or blow-molded. Their distinguishing features include: Extremely low levels of metals Extremely low levels of fluoride ion and other anions Excellent chemical resistance and temperature capability up to 260°C UHP packaged to assure clean, contamination-free product Information provided by Dyneon, A 3M Company

Order this product through the following link:

http://www.lookpolymers.com/polymer_3M-Dyneon-PFA-6515-UHPZ-Perfluoroalkoxy-Fluorothermoplastic-Granules.php

Physical Properties	Metric	English	Comments
Specific Gravity	2.15 g/cc	2.15 g/cc	ASTM D792
Melt Index of Compound	15 g/10 min @Load 5.00 kg, Temperature 372 °C	15 g/10 min @Load 11.0 lb, Temperature 702 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	60	60	ASTM D2240
Tensile Strength at Break	30.0 MPa	4350 psi	ASTM D638
Elongation at Break	450 %	450 %	ASTM D638
Flexural Modulus	0.620 GPa	89.9 ksi	ASTM D790

Thermal Properties	Metric	English	Comments
Melting Point	310 °C	590 °F	ASTM D4591
Maximum Service Temperature, Air	260 °C	500 °F	
Flammability, UL94	V-0	V-0	
Oxygen Index	>= 95 %	>= 95 %	ASTM D2863

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China