

3M Dyneon™ TF 2021 PTFE (discontinued **)

Category : Polymer , Thermoplastic , Fluoropolymer , PTFE

Material Notes:

Processable by standard paste extrusion methods Both grades can be processed at low to medium reduction ratios TF 2021 PTFE is preferred for unsintered thread sealing tapes and expanded joint sealants TF 2025 PTFE is recommended for pipe liner and applications because of its superior green strength Information provided by Dyneon, A 3M Company

Order this product through the following link:

http://www.lookpolymers.com/polymer_3M-Dyneon-TF-2021-PTFE-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Bulk Density	0.510 g/cc	0.0184 lb/in ³	ISO 12086
Density	2.15 g/cc	0.0777 lb/in ³	ISO 12086
Particle Size	500 µm	500 µm	average; ISO 12086
Thickness	1600 microns	63.0 mil	ASTM D4895

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	28.0 MPa	4060 psi	ISO 12086
Elongation at Break	340 %	340 %	ISO 12086

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+19 ohm-cm	1.00e+19 ohm-cm	IEC 60093
Surface Resistance	1.00e+18 ohm	1.00e+18 ohm	IEC 60093

Descriptive Properties	Value	Comments
Extrusion Pressure	30 MPa	reduction ratio 400, ASTM D4894
Reduction Ratio Range	20-500:1	Dyneon Method

Contact Songhan Plastic Technology Co.,Ltd.Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China