## 3M Dyneon<sup>™</sup> TF 2029 PTFE Paste Extrusion Powder (discontinued \*\*)

Category : Polymer , Thermoplastic , Fluoropolymer , PTFE , Polytetrafluoroethylene (PTFE), Extruded

## Material Notes:

Type I PTFE. Free flowing powder. Minimum reduction ratio is 5; Max is 100. Average particle size 500 µm. Used for electrical insulating tapes, liners, and yarns.Dyneon offers a family of PTFE fine powder paste extrusion resins. These products are well suited for a variety of applications, including tubing, hose, pipe liners, tapes, wire and cable, diaphragms and textile/fiber. Available grades are designed to balance process properties such as reduction ratio, and performance properties, such as tensile strength, shrinkage, flex life and permeations. Data provided by Dyneon.

## Order this product through the following link: http://www.lookpolymers.com/polymer\_3M-Dyneon-TF-2029-PTFE-Paste-Extrusion-Powder-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	2.15 g/cc	0.0777 lb/in³	Sintered moldings; ASTM D4894/D4895
Apparent Bulk Density	0.480 g/cc	0.0173 lb/in <sup>3</sup>	DIN 53 466

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	28.0 MPa	4060 psi	Sintered moldings; ASTM D4894/4895
	@Thickness 1.60 mm	@Thickness 0.0630 in	
Elongation at Break	340 %	340 %	Sintered Molding; ASTM D4894

Electrical Properties	Metric	English	Comments
Electrical Resistivity	1.00e+14 ohm-cm	1.00e+14 ohm-cm	IEC 60093
Surface Resistance	1.00e+17 ohm	1.00e+17 ohm	IEC 60093

## Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com Email : sales@lookpolymers.com Tel : +86 021-51131842 Mobile : +86 13061808058 Skype : lookpolymers Address : United North Road 215,Fengxian District, Shanghai City,China