

## **3M S38 Glass Bubbles**

Category: Ceramic, Glass

## **Material Notes:**

3M™ Glass Bubbles are engineered hollow glass microspheres that are alternatives to conventional fillers and additives such as silicas, calcium carbonate, talc, clay, etc., for many demanding applications. These low-density particles are used in a wide range of industries to reduce part weight, lower costs and enhance product properties. The unique spherical shape of 3M glass bubbles offers a number of important benefits, including: higher filler loading, lower viscosity/improved flow and reduced shrinkage and warpage. It also helps the 3M glass bubbles blend readily into compounds and makes them adaptable to a variety of production processes including spraying, casting and molding. The chemically stable soda-lime-borosilicate glass composition of 3M glass bubbles provides excellent water resistance to create more stable emulsions. They are also non-combustible and nonporous, so they do not absorb resin. And, their low alkalinity gives 3M glass bubbles compatibility with most resins, stable viscosity and long shelf life.Information provided by 3M

Order this product through the following link: http://www.lookpolymers.com/polymer\_3M-S38-Glass-Bubbles.php

Physical Properties	Metric	English	Comments
Density	0.350 - 0.410 g/cc	0.0126 - 0.0148 lb/in³	
	0.380 g/cc	0.0137 lb/in³	
Volatiles	0.50 %	0.50 %	
Particle Size	15 µm	15 µm	10th%
	40 μm	40 μm	50th%
	75 µm	75 µm	90th%
	85 µm	85 µm	Effective Top Size

Mechanical Properties	Metric	English	Comments
Compressive Strength	27.6 MPa	4000 psi	

Thermal Properties	Metric	English	Comments
Thermal Conductivity	0.127 W/m-K	0.881 BTU-in/hr-ft <sup>2</sup> -°F	
Maximum Service Temperature, Air	600 °C	1110 °F	

Electrical Properties	Metric	English	Comments
	1.2 - 2.0	1.2 - 2.0	
Dielectric Constant	@Frequency 1.00e+8 Hz	@Frequency 1.00e+8 Hz	



Descriptive Properties	Value	Comments
Alkalinity	<0.5 milliequivalents/gram	
Appearance	White	unaided eye
Chemical Resistance	soda-lime-borosilicate glass	
Oil Absorption	0.2-0.6 g oil/100 cc	ASTM D1483

## **Contact Songhan Plastic Technology Co.,Ltd.**

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China