

## 3M Scotch-Grip™/Fastbond™ 5497 Industrial Adhesive (discontinued \*\*)

Category: Polymer, Adhesive, Thermoset, Polyurethane, TS, Thermoset Polyurethane, Adhesive

## **Material Notes:**

An adhesive with versatile substrate and application capabilities for a wide range of industrial product assembly applications. One part, 100% solids moisture curing liquid urethane adhesive which can bond wood, metal and many plastics without primers. Sets to handling strength in 30 to 60 minutes. The solids weight is approximately 100%. The flash point is greater than 300°F/greater than -149°C. The color is clear, the consistency is thick liquid, and the application method is flow or trowel. The bond range holds 5 minutes. Information provided by 3M Adhesives Division.

## Order this product through the following link:

http://www.lookpolymers.com/polymer\_3M-Scotch-GripFastbond-5497-Industrial-Adhesive-nbspdiscontinued-.php

Mechanical Properties	Metric	English	Comments
Adhesive Bond Strength	0.210 MPa	30.5 psi	Maple to itself at 50% R.H. Test at 0.1 inches/min. separation rate.
	@Temperature 23.9 °C	@Temperature 75.0 °F	

Processing Properties	Metric	English	Comments
Processing Temperature	20.0 °C	68.0 °F	

## Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China