

## 3M Scotch-Weld™ Medium Instant Wood Adhesives and Surface Activator

Category : Polymer , Adhesive

### Material Notes:

3M™ Scotch-Weld™ Instant Wood Adhesives an Surface Activator are single component, room temperature-curing adhesives that provides cure and speed and shear strength for demanding applications in the manufacture and repair of furniture, cabinets, and other wood products. Information provided by 3M

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_3M-Scotch-Weld-Medium-Instant-Wood-Adhesives-and-Surface-Activator.php](http://www.lookpolymers.com/polymer_3M-Scotch-Weld-Medium-Instant-Wood-Adhesives-and-Surface-Activator.php)

Physical Properties	Metric	English	Comments
Viscosity	>= 450 cP	>= 450 cP	

Mechanical Properties	Metric	English	Comments
Shear Strength	2.07 MPa	300 psi	Overlap, Particleboard, Substrate Failure
	2.76 MPa	400 psi	Overlap, Melamine, Substrate Failure
	3.10 MPa	450 psi	Overlap, Pine, Substrate/Cohesive Failure
	3.10 MPa	450 psi	Overlap, MDF, Cohesive Failure
	3.45 MPa	500 psi	Overlap, Polyurethane Finish, Adhesive Failure
	4.14 MPa	600 psi	Overlap, Polyacrylic Finish, Cohesive Failure
	6.21 MPa	900 psi	Overlap, Poplar, Substrate/Cohesive Failure
	6.21 MPa	900 psi	Overlap, High Pressure Laminate, Substrate Failure
	6.89 MPa	1000 psi	Overlap, Plywood, Cohesive Failure
	7.24 MPa	1050 psi	Overlap, Maple, Substrate Failure
	13.4 MPa	1950 psi	Overlap, Aluminum, Adhesive Failure
	16.2 MPa	2350 psi	Overlap, Oak, Substrate/Cohesive Failure
	19.7 MPa	2850 psi	Overlap, Steel, Adhesive Failure
	3.10 MPa	450 psi	Overlap, Aluminum, 90% RH, Adhesive Failure
	@Temperature 32.0 °C	@Temperature 89.6 °F	
3.79 MPa	550 psi	Overlap, Polyurethane Finish, 90% RH, Adhesive Failure	

Mechanical Properties	@Temperature 32.0 °C Metric	@Temperature 89.6 °F English	Comments
	4.14 MPa	600 psi	Overlap, Pine, 90% RH, Adhesive Failure
	@Temperature 32.0 °C	@Temperature 89.6 °F	
	6.55 MPa	950 psi	Overlap, Plywood, 90% RH, Substrate Failure
	@Temperature 32.0 °C	@Temperature 89.6 °F	
	6.89 MPa	1000 psi	Overlap, Polyurethane Finish, Adhesive Failure
	@Temperature 66.0 °C	@Temperature 151 °F	
	7.24 MPa	1050 psi	Overlap, Plywood, Substrate Failure
	@Temperature 66.0 °C	@Temperature 151 °F	
	7.24 MPa	1050 psi	Overlap, Aluminum, Adhesive Failure
	@Temperature 66.0 °C	@Temperature 151 °F	
	7.58 MPa	1100 psi	Overlap, Pine, Adhesive Failure
	@Temperature 66.0 °C	@Temperature 151 °F	
	12.8 MPa	1850 psi	Overlap, Oak, Substrate/Adhesive Failure
	@Temperature 66.0 °C	@Temperature 151 °F	
	13.4 MPa	1950 psi	Overlap, Oak, 90% RH, Substrate/Adhesive Failure
	@Temperature 32.0 °C	@Temperature 89.6 °F	

Processing Properties	Metric	English	Comments
Cure Time	1440 min	24.0 hour	Full Cure

Descriptive Properties	Value	Comments
Appearance	Clear-Slightly yellow liquid	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China