

## 3M Weatherban™ PF5422 Ribbon Sealant

Category : Polymer

**Material Notes:**

3M™ Weatherban™ Ribbon Sealants PF 5422 and PF 5423 are a supported synthetic rubber sealant in ribbon form. They offer a watertight, gasket-like seal in applications such as bedding glass, around window and door frames, etc. They can also act as a metal seam sealer in overlap seams, building panels, rain gutters, and can be used in conjunction with mechanical fasteners. They offer outstanding resistance to weathering, and develops good adhesion to glass, metal, and most other surfaces. Features: Protective liner and sealant are different widths for easy release. Maintain tack at temperatures as low as 40°F (5°C) permitting application in unheated area. Stays in position on vertical or overhead surfaces. Easy hand layup – no special equipment needed. Repositionable during application. Builds aggressive adhesion with time. Solvent-free. No shrinkage. Vibration and sound dampening qualities. Helps prevent bimetallic (galvanic cell action) corrosion, when placed between metal surfaces. May be positioned side by side to achieve varying widths. Information provided by 3M

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_3M-Weatherban-PF5422-Ribbon-Sealant.php](http://www.lookpolymers.com/polymer_3M-Weatherban-PF5422-Ribbon-Sealant.php)

Physical Properties	Metric	English	Comments
Density	1.52 g/cc	0.0549 lb/in <sup>3</sup>	
Solids Content	100 %	100 %	

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	30	30	
Tensile Strength at Break	0.228 MPa	33.1 psi	5"/Min
Elongation at Break	200 %	200 %	5"/Min

Processing Properties	Metric	English	Comments
Shelf Life	24.0 Month	24.0 Month	

Descriptive Properties	Value	Comments
Color	Black	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China

