

A. Schulman ComAlloy Aqualoy® 150 Polypropylene, Glass Reinforced, Chemically Coupled NSF

Category : Polymer , Thermoplastic , Polypropylene (PP)

Material Notes:

Data provided by the manufacturer, ComAlloy International Company. 50% Glass Reinforced. In Aqualoy® materials, carefully selected base resins and proprietary additives meld hydrolytic stability and high strength traits into a unique property blend. The ComAlloy product line has been integrated into the A Schulman product line.

Order this product through the following link:

http://www.lookpolymers.com/polymer_A-Schulman-ComAlloy-Aqualoy-150-Polypropylene-Glass-Reinforced-Chemically-Coupled-NSF.php

Physical Properties	Metric	English	Comments
Density	1.32 g/cc	0.0477 lb/in ³	
Linear Mold Shrinkage	0.0010 cm/cm	0.0010 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	109	109	ASTM D785
Tensile Strength, Ultimate	107 MPa	15500 psi	ASTM D638
Elongation at Break	2.0 %	2.0 %	ASTM D638
Flexural Strength	153 MPa	22200 psi	ASTM D790
Flexural Modulus	9.00 GPa	1310 ksi	ASTM D790
Izod Impact, Notched	1.23 J/cm	2.30 ft-lb/in	ASTM D256
Izod Impact, Unnotched	6.99 J/cm	13.1 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	164 °C	327 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	153 °C	307 °F	ASTM D648

Processing Properties	Metric	English	Comments
Middle Barrel Temperature	229 - 246 °C	444 - 475 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China