

## A. Schulman ComAlloy Comtuf® 104 Polypropylene, Glass Reinforced, Chemically Coupled, Impact Modified, UL

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene, Glass Reinforced, Impact Modified

### Material Notes:

Data provided by the manufacturer, ComAlloy International Company. 25% Glass Reinforced. Superior toughness and impact resistance characterize Comtuf® materials. The ComAlloy product line has been integrated into the A Schulman product line.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_A-Schulman-ComAlloy-Comtuf-104-Polypropylene-Glass-Reinforced-Chemically-Coupled-Impact-Modified-UL.php](http://www.lookpolymers.com/polymer_A-Schulman-ComAlloy-Comtuf-104-Polypropylene-Glass-Reinforced-Chemically-Coupled-Impact-Modified-UL.php)

Physical Properties	Metric	English	Comments
Density	1.08 g/cc	0.0390 lb/in <sup>3</sup>	
Linear Mold Shrinkage	0.0040 cm/cm	0.0040 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	97	97	ASTM D785
Tensile Strength, Ultimate	49.0 MPa	7110 psi	ASTM D638
Elongation at Break	5.1 %	5.1 %	ASTM D638
Flexural Strength	75.0 MPa	10900 psi	ASTM D790
Flexural Modulus	3.30 GPa	479 ksi	ASTM D790
Izod Impact, Notched	0.800 J/cm	1.50 ft-lb/in	ASTM D256
Izod Impact, Unnotched	4.59 J/cm	8.60 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	157 °C	315 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	125 °C	257 °F	ASTM D648

Processing Properties	Metric	English	Comments
Middle Barrel Temperature	229 - 246 °C	444 - 475 °F	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215,Fengxian District, Shanghai City,China**