

A. Schulman ComAlloy Comtuf® 611 Nylon 6, Glass Reinforced, Impact Modified

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6, Glass Filled, Impact Grade

Material Notes:

Data provided by the manufacturer, ComAlloy International Company. 13% Glass Reinforced. Superior toughness and impact resistance characterize Comtuf® materials. The ComAlloy product line has been integrated into the A Schulman product line.

Order this product through the following link:

http://www.lookpolymers.com/polymer_A-Schulman-ComAlloy-Comtuf-611-Nylon-6-Glass-Reinforced-Impact-Modified.php

Physical Properties	Metric	English	Comments
Density	1.19 g/cc	0.0430 lb/in ³	
Linear Mold Shrinkage	0.0080 cm/cm	0.0080 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	118	118	ASTM D785
Tensile Strength, Ultimate	84.0 MPa	12200 psi	ASTM D638
Elongation at Break	3.0 %	3.0 %	ASTM D638
Flexural Strength	128 MPa	18600 psi	ASTM D790
Flexural Modulus	4.30 GPa	624 ksi	ASTM D790
Izod Impact, Notched	0.640 J/cm	1.20 ft-lb/in	ASTM D256
Izod Impact, Unnotched	5.82 J/cm	10.9 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Melting Point	205 - 225 °C	401 - 437 °F	
Deflection Temperature at 0.46 MPa (66 psi)	196 °C	385 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	157 °C	315 °F	ASTM D648

Processing Properties	Metric	English	Comments
Middle Barrel Temperature	260 - 271 °C	500 - 520 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China