

A. Schulman ComAlloy Hiloy® 102 Polypropylene, Glass Reinforced

Category : Polymer , Thermoplastic , Polypropylene (PP)

Material Notes:

Data provided by the manufacturer, ComAlloy International Company.20% Glass Reinforced.The ComAlloy product line has been integrated into the A Schulman product line.

Order this product through the following link:

http://www.lookpolymers.com/polymer_A-Schulman-ComAlloy-Hiloy-102-Polypropylene-Glass-Reinforced.php

Physical Properties	Metric	English	Comments
Density	1.04 g/cc	0.0376 lb/in ³	
Linear Mold Shrinkage	0.0050 cm/cm	0.0050 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	99	99	ASTM D785
Tensile Strength, Ultimate	56.0 MPa	8120 psi	ASTM D638
Elongation at Break	4.2 %	4.2 %	ASTM D638
Flexural Strength	71.0 MPa	10300 psi	ASTM D790
Flexural Modulus	2.60 GPa	377 ksi	ASTM D790
Izod Impact, Notched	0.530 J/cm	0.993 ft-lb/in	ASTM D256
Izod Impact, Unnotched	3.20 J/cm	5.99 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	164 °C	327 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	116 °C	241 °F	ASTM D648

Processing Properties	Metric	English	Comments
Middle Barrel Temperature	229 - 246 °C	444 - 475 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China