

## A. Schulman ComAlloy Hiloy® 131 Polypropylene, Glass/Mineral Reinforced, Chemically Coupled

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene, Glass/Mineral Reinforced

### Material Notes:

Data provided by the manufacturer, ComAlloy International Company.50% Glass/Mineral Reinforced.The ComAlloy product line has been integrated into the A Schulman product line.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_A-Schulman-ComAlloy-Hiloy-131-Polypropylene-GlassMineral-Reinforced-Chemically-Coupled.php](http://www.lookpolymers.com/polymer_A-Schulman-ComAlloy-Hiloy-131-Polypropylene-GlassMineral-Reinforced-Chemically-Coupled.php)

| Physical Properties   | Metric       | English                   | Comments  |
|-----------------------|--------------|---------------------------|-----------|
| Density               | 1.17 g/cc    | 0.0423 lb/in <sup>3</sup> |           |
| Linear Mold Shrinkage | 0.0050 cm/cm | 0.0050 in/in              | ASTM D955 |

| Mechanical Properties      | Metric    | English       | Comments  |
|----------------------------|-----------|---------------|-----------|
| Hardness, Rockwell R       | 86        | 86            | ASTM D785 |
| Tensile Strength, Ultimate | 46.0 MPa  | 6670 psi      | ASTM D638 |
| Elongation at Break        | 4.0 %     | 4.0 %         | ASTM D638 |
| Flexural Strength          | 68.0 MPa  | 9860 psi      | ASTM D790 |
| Flexural Modulus           | 3.00 GPa  | 435 ksi       | ASTM D790 |
| Izod Impact, Notched       | 1.23 J/cm | 2.30 ft-lb/in | ASTM D256 |
| Izod Impact, Unnotched     | 5.23 J/cm | 9.80 ft-lb/in | ASTM D256 |

| Thermal Properties                          | Metric | English | Comments  |
|---------------------------------------------|--------|---------|-----------|
| Deflection Temperature at 0.46 MPa (66 psi) | 164 °C | 327 °F  | ASTM D648 |
| Deflection Temperature at 1.8 MPa (264 psi) | 138 °C | 280 °F  | ASTM D648 |

| Processing Properties  | Metric | English | Comments                               |
|------------------------|--------|---------|----------------------------------------|
| Processing Temperature | 225 °C | 437 °F  | Approximate middle barrel temperature. |

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215,Fengxian District, Shanghai City,China**