

A. Schulman ComAlloy Hiloy® 515 Polycarbonate, Carbon Fiber Reinforced

Category : Polymer , Thermoplastic , Polycarbonate (PC) , Polycarbonate, Carbon Fiber Reinforced

Material Notes:

Data provided by the manufacturer, ComAlloy International Company. 10% Carbon Fiber Reinforced. The ComAlloy product line has been integrated into the A Schulman product line.

Order this product through the following link:

http://www.lookpolymers.com/polymer_A-Schulman-ComAlloy-Hiloy-515-Polycarbonate-Carbon-Fiber-Reinforced.php

Physical Properties	Metric	English	Comments
Density	1.25 g/cc	0.0452 lb/in ³	
Linear Mold Shrinkage	0.0020 cm/cm	0.0020 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	120	120	ASTM D785
Tensile Strength, Ultimate	105 MPa	15200 psi	ASTM D638
Elongation at Break	3.0 %	3.0 %	ASTM D638
Flexural Strength	148 MPa	21500 psi	ASTM D790
Flexural Modulus	7.60 GPa	1100 ksi	ASTM D790
Izod Impact, Notched	0.480 J/cm	0.899 ft-lb/in	ASTM D256
Izod Impact, Unnotched	2.94 J/cm	5.51 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	149 °C	300 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	143 °C	289 °F	ASTM D648
Glass Transition Temp, Tg	145 - 150 °C	293 - 302 °F	

Processing Properties	Metric	English	Comments
Processing Temperature	310 °C	590 °F	Approximate middle barrel temperature.

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China