

## A. Schulman ComAlloy Hiloy® 614 Nylon 6, Glass Reinforced

Category : Polymer , Thermoplastic , Nylon , Nylon 6

**Material Notes:**

Data provided by the manufacturer, ComAlloy International Company.45% Glass Reinforced.The ComAlloy product line has been integrated into the A Schulman product line.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_A-Schulman-ComAlloy-Hiloy-614-Nylon-6-Glass-Reinforced.php](http://www.lookpolymers.com/polymer_A-Schulman-ComAlloy-Hiloy-614-Nylon-6-Glass-Reinforced.php)

Physical Properties	Metric	English	Comments
Density	1.50 g/cc	0.0542 lb/in <sup>3</sup>	
Linear Mold Shrinkage	0.0020 cm/cm	0.0020 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	118	118	ASTM D785
Tensile Strength, Ultimate	202 MPa	29300 psi	ASTM D638
Elongation at Break	3.0 %	3.0 %	ASTM D638
Flexural Strength	322 MPa	46700 psi	ASTM D790
Flexural Modulus	12.5 GPa	1810 ksi	ASTM D790
Izod Impact, Notched	1.76 J/cm	3.30 ft-lb/in	ASTM D256
Izod Impact, Unnotched	NB	NB	ASTM D256

Thermal Properties	Metric	English	Comments
Melting Point	205 - 225 °C	401 - 437 °F	
Deflection Temperature at 0.46 MPa (66 psi)	230 °C	446 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	214 °C	417 °F	ASTM D648

Processing Properties	Metric	English	Comments
Middle Barrel Temperature	260 - 271 °C	500 - 520 °F	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215, Fengxian District, Shanghai City, China**