

A. Schulman ComAlloy Hiloy® 625 Nylon 6/6, Glass Reinforced

Category : Polymer , Thermoplastic , Nylon , Nylon 66

Material Notes:

Data provided by the manufacturer, ComAlloy International Company.50% Glass Reinforced.The ComAlloy product line has been integrated into the A Schulman product line.

Order this product through the following link:

http://www.lookpolymers.com/polymer_A-Schulman-ComAlloy-Hiloy-625-Nylon-66-Glass-Reinforced.php

Physical Properties	Metric	English	Comments
Density	1.55 g/cc	0.0560 lb/in ³	
Linear Mold Shrinkage	0.0020 cm/cm	0.0020 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	121	121	ASTM D785
Tensile Strength, Ultimate	195 MPa	28300 psi	ASTM D638
Elongation at Break	3.0 %	3.0 %	ASTM D638
Flexural Strength	319 MPa	46300 psi	ASTM D790
Flexural Modulus	13.8 GPa	2000 ksi	ASTM D790
Izod Impact, Notched	1.39 J/cm	2.60 ft-lb/in	ASTM D256
Izod Impact, Unnotched	NB	NB	ASTM D256

Thermal Properties	Metric	English	Comments
Melting Point	255 - 275 °C	491 - 527 °F	
Deflection Temperature at 0.46 MPa (66 psi)	268 °C	514 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	260 °C	500 °F	ASTM D648

Processing Properties	Metric	English	Comments
Middle Barrel Temperature	271 - 285 °C	520 - 545 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China