

A. Schulman ComAlloy Hiloy® 633 Nylon 6/6, Glass Reinforced, Flow Enhanced, UL

Category : Polymer , Thermoplastic , Nylon , Nylon 66

Material Notes:

Data provided by the manufacturer, ComAlloy International Company.33% Glass Reinforced.The ComAlloy product line has been integrated into the A Schulman product line.

Order this product through the following link:

http://www.lookpolymers.com/polymer_A-Schulman-ComAlloy-Hiloy-633-Nylon-66-Glass-Reinforced-Flow-Enhanced-UL.php

Physical Properties	Metric	English	Comments
Density	1.32 g/cc	0.0477 lb/in ³	
Linear Mold Shrinkage	0.0020 cm/cm	0.0020 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	120	120	ASTM D785
Tensile Strength, Ultimate	166 MPa	24100 psi	ASTM D638
Elongation at Break	4.0 %	4.0 %	ASTM D638
Flexural Strength	228 MPa	33100 psi	ASTM D790
Flexural Modulus	7.60 GPa	1100 ksi	ASTM D790
Izod Impact, Notched	0.960 J/cm	1.80 ft-lb/in	ASTM D256
Izod Impact, Unnotched	6.30 J/cm	11.8 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Melting Point	255 - 275 °C	491 - 527 °F	
Deflection Temperature at 0.46 MPa (66 psi)	220 °C	428 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	210 °C	410 °F	ASTM D648

Processing Properties	Metric	English	Comments
Middle Barrel Temperature	271 - 285 °C	520 - 545 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China