

## A. Schulman ComAlloy Hiloy® 662 Nylon 6, Glass Bead Reinforced

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6, Glass Bead Filled

### Material Notes:

Data provided by the manufacturer, ComAlloy International Company.20% Glass Bead Reinforced.The ComAlloy product line has been integrated into the A Schulman product line.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_A-Schulman-ComAlloy-Hiloy-662-Nylon-6-Glass-Bead-Reinforced.php](http://www.lookpolymers.com/polymer_A-Schulman-ComAlloy-Hiloy-662-Nylon-6-Glass-Bead-Reinforced.php)

Physical Properties	Metric	English	Comments
Density	1.25 g/cc	0.0452 lb/in <sup>3</sup>	
Linear Mold Shrinkage	0.011 cm/cm	0.011 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	110	110	ASTM D785
Tensile Strength, Ultimate	60.0 MPa	8700 psi	ASTM D638
Elongation at Break	12 %	12 %	ASTM D638
Flexural Strength	83.0 MPa	12000 psi	ASTM D790
Flexural Modulus	3.00 GPa	435 ksi	ASTM D790
Izod Impact, Notched	0.690 J/cm	1.29 ft-lb/in	ASTM D256
Izod Impact, Unnotched	5.23 J/cm	9.80 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Melting Point	205 - 225 °C	401 - 437 °F	
Deflection Temperature at 0.46 MPa (66 psi)	172 °C	342 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	106 °C	223 °F	ASTM D648

Processing Properties	Metric	English	Comments
Middle Barrel Temperature	260 - 271 °C	500 - 520 °F	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China