

A. Schulman ComAlloy Lubrilon® 628 Nylon 6/6, Glass Fiber/Molybdenum Disulfide Filled, Flow Enhanced

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, Glass Fiber/MoS2 Filled

Material Notes:

Data provided by the manufacturer, ComAlloy International Company. High performance and excellent lubricity with minimal surface wear. The ComAlloy product line has been integrated into the A Schulman product line.

Order this product through the following link:

http://www.lookpolymers.com/polymer_A-Schulman-ComAlloy-Lubrilon-628-Nylon-66-Glass-FiberMolybdenum-Disulfide-Filled-Flow-Enhanced.php

Physical Properties	Metric	English	Comments
Density	1.43 g/cc	0.0517 lb/in ³	
Linear Mold Shrinkage	0.0030 cm/cm	0.0030 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	118	118	ASTM D785
Tensile Strength, Ultimate	152 MPa	22000 psi	ASTM D638
Elongation at Break	4.0 %	4.0 %	ASTM D638
Flexural Strength	241 MPa	35000 psi	ASTM D790
Flexural Modulus	10.0 GPa	1450 ksi	ASTM D790
Izod Impact, Notched	0.850 J/cm	1.59 ft-lb/in	ASTM D256
Izod Impact, Unnotched	3.74 J/cm	7.01 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Melting Point	255 - 275 °C	491 - 527 °F	
Deflection Temperature at 0.46 MPa (66 psi)	253 °C	487 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	194 °C	381 °F	ASTM D648

Processing Properties	Metric	English	Comments
Middle Barrel Temperature	271 - 285 °C	520 - 545 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China