

A. Schulman ComAlloy Voloy® 461 Glass Reinforced, PBT Alloy, Flame Retardant, UL

Category : Polymer , Thermoplastic , Polyester, TP , Polybutylene Terephthalate (PBT)

Material Notes:

Data provided by the manufacturer, ComAlloy International Company.30% Glass Reinforced.The ComAlloy product line has been integrated into the A Schulman product line.

Order this product through the following link:

http://www.lookpolymers.com/polymer_A-Schulman-ComAlloy-Voloy-461-Glass-Reinforced-PBT-Alloy-Flame-Retardant-UL.php

Physical Properties	Metric	English	Comments
Density	1.63 g/cc	0.0589 lb/in ³	
Linear Mold Shrinkage	0.0020 cm/cm	0.0020 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	120	120	ASTM D785
Tensile Strength, Ultimate	119 MPa	17300 psi	ASTM D638
Elongation at Break	2.8 %	2.8 %	ASTM D638
Flexural Strength	183 MPa	26500 psi	ASTM D790
Flexural Modulus	9.50 GPa	1380 ksi	ASTM D790
Izod Impact, Notched	0.800 J/cm	1.50 ft-lb/in	ASTM D256
Izod Impact, Unnotched	6.73 J/cm	12.6 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Melting Point	210 - 225 °C	410 - 437 °F	
Deflection Temperature at 0.46 MPa (66 psi)	122 °C	252 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	90.0 °C	194 °F	ASTM D648

Processing Properties	Metric	English	Comments
Middle Barrel Temperature	235 - 249 °C	455 - 480 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China