

## A. Schulman ComAlloy Voloy® 631 Nylon 6/6, Glass Reinforced, Flow Enhanced, Flame Retardant, UL

Category : Polymer , Thermoplastic , Nylon , Nylon 66

### Material Notes:

Data provided by the manufacturer, ComAlloy International Company. 13% Glass Reinforced. The ComAlloy product line has been integrated into the A Schulman product line.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_A-Schulman-ComAlloy-Voloy-631-Nylon-66-Glass-Reinforced-Flow-Enhanced-Flame-Retardant-UL.php](http://www.lookpolymers.com/polymer_A-Schulman-ComAlloy-Voloy-631-Nylon-66-Glass-Reinforced-Flow-Enhanced-Flame-Retardant-UL.php)

Physical Properties	Metric	English	Comments
Density	1.45 g/cc	0.0524 lb/in <sup>3</sup>	
Linear Mold Shrinkage	0.0050 cm/cm	0.0050 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	118	118	ASTM D785
Tensile Strength, Ultimate	97.0 MPa	14100 psi	ASTM D638
Elongation at Break	4.0 %	4.0 %	ASTM D638
Flexural Strength	156 MPa	22600 psi	ASTM D790
Flexural Modulus	6.20 GPa	899 ksi	ASTM D790
Izod Impact, Notched	0.370 J/cm	0.693 ft-lb/in	ASTM D256
Izod Impact, Unnotched	2.35 J/cm	4.40 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Melting Point	255 - 275 °C	491 - 527 °F	
Deflection Temperature at 0.46 MPa (66 psi)	210 °C	410 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	200 °C	392 °F	ASTM D648

Processing Properties	Metric	English	Comments
Middle Barrel Temperature	271 - 285 °C	520 - 545 °F	

**Contact Songhan Plastic Technology Co.,Ltd.**

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China