

## A. Schulman ComAlloy Voloy® 681 Nylon 6/6, Glass Fiber/Bead Reinforced, Nylon 6/6 Alloy, Flame Retardant, UL

Category : Polymer , Thermoplastic , Nylon , Nylon 66

### Material Notes:

Data provided by the manufacturer, ComAlloy International Company.45% Glass Fiber/Bead Reinforced. Halogen- and phosphorous-freeThe ComAlloy product line has been integrated into the A Schulman product line.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_A-Schulman-ComAlloy-Voloy-681-Nylon-66-Glass-FiberBead-Reinforced-Nylon-66-Alloy-Flame-Retardant-UL.php](http://www.lookpolymers.com/polymer_A-Schulman-ComAlloy-Voloy-681-Nylon-66-Glass-FiberBead-Reinforced-Nylon-66-Alloy-Flame-Retardant-UL.php)

Physical Properties	Metric	English	Comments
Density	1.73 g/cc	0.0625 lb/in <sup>3</sup>	
Linear Mold Shrinkage	0.0030 cm/cm	0.0030 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	118	118	ASTM D785
Tensile Strength, Ultimate	66.0 MPa	9570 psi	ASTM D638
Elongation at Break	2.0 %	2.0 %	ASTM D638
Flexural Strength	90.0 MPa	13100 psi	ASTM D790
Flexural Modulus	6.20 GPa	899 ksi	ASTM D790
Izod Impact, Notched	0.530 J/cm	0.993 ft-lb/in	ASTM D256
Izod Impact, Unnotched	1.60 J/cm	3.00 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Melting Point	255 - 275 °C	491 - 527 °F	
Deflection Temperature at 0.46 MPa (66 psi)	260 °C	500 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	232 °C	450 °F	ASTM D648

Processing Properties	Metric	English	Comments
Middle Barrel Temperature	271 - 285 °C	520 - 545 °F	

**Contact Songhan Plastic Technology Co.,Ltd.**

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China