

A. Schulman FORMION™ FI 330 Ionomer

Category : Polymer , Thermoplastic , Ionomer

Material Notes:

Information provided by A. Schulman.

Order this product through the following link:

http://www.lookpolymers.com/polymer_A-Schulman-FORMION-FI-330-Ionomer.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.15 g/cc	1.15 g/cc	ISO 1183/1
Linear Mold Shrinkage	0.0020 - 0.0060 cm/cm @Thickness 3.20 mm	0.0020 - 0.0060 in/in @Thickness 0.126 in	72 hr; ISO 294

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	60	60	15 sec delay; ISO 868
Tensile Strength, Ultimate	15.0 MPa	2180 psi	at max load; ISO 527
Elongation at Break	150 %	150 %	ISO 527
Flexural Modulus	0.911 GPa	132 ksi	Tangent; ISO 178

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	63.0 °C @Thickness 3.20 mm	145 °F @Thickness 0.126 in	ISO 75

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China