

A. Schulman POLYFORT™ FPP 1606 Glass Filled Chemically Coupled Impact Copolymer Polypropylene

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 30% Glass Fiber Filler

Material Notes:

Description Polyfort® FPP 1606 is a 30% glass filled chemically coupled impact copolymer polypropylene product. Information provided by A. Schulman.

Order this product through the following link:

http://www.lookpolymers.com/polymer_A-Schulman-POLYFORT-FPP-1606-Glass-Filled-Chemically-Coupled-Impact-Copolymer-Polypropylene.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.12 g/cc	1.12 g/cc	ASTM D792
Melt Flow	18 g/10 min	18 g/10 min	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	110	110	ASTM D785
Tensile Strength, Yield	70.0 MPa	10200 psi	ASTM D638
Elongation at Break	2.0 %	2.0 %	ASTM D638
Flexural Strength	100 MPa	14500 psi	ASTM D790
Flexural Modulus	4.50 GPa	653 ksi	ASTM D790
Izod Impact, Notched	1.50 J/cm	2.81 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	155 °C	311 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	140 °C	284 °F	ASTM D648

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China