

## A. Schulman POLYFORT™ FPP 3708U UV Stable Copolymer Polypropylene

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 20% Calcium Carbonate (CaCO3) Filler

### Material Notes:

Description Polyfort® FPP 3708U is a 20% CAC03 filled UV stable copolymer polypropylene. Information provided by A. Schulman.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_A-Schulman-POLYFORT-FPP-3708U-UV-Stable-Copolymer-Polypropylene.php](http://www.lookpolymers.com/polymer_A-Schulman-POLYFORT-FPP-3708U-UV-Stable-Copolymer-Polypropylene.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.05 g/cc	1.05 g/cc	ASTM D792
Melt Flow	20 g/10 min	20 g/10 min	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	17.0 MPa	2470 psi	ASTM D638
Elongation at Break	10 %	10 %	ASTM D638
Flexural Strength	27.0 MPa	3920 psi	ASTM D790
Flexural Modulus	1.40 GPa	203 ksi	ASTM D790
Izod Impact, Notched	1.90 J/cm	3.56 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	80.0 °C	176 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	50.0 °C	122 °F	ASTM D648

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China