

A. Schulman SCHULAMID® 66 GF33H 33% Glass Fiber Reinforced, Heat Stabilized Nylon 66

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, 30% Glass Fiber Filled

Material Notes:

Information provided by A. Schulman.

Order this product through the following link:

http://www.lookpolymers.com/polymer_A-Schulman-SCHULAMID-66-GF33H-33-Glass-Fiber-Reinforced-Heat-Stabilized-Nylon-66.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.40 g/cc	1.40 g/cc	ASTM D792
Linear Mold Shrinkage	0.0040 cm/cm @Thickness 3.175 mm	0.0040 in/in @Thickness 0.1250 in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	169 MPa	24500 psi	ASTM D638
Elongation at Break	5.0 %	5.0 %	ASTM D638
Flexural Strength	225 MPa	32700 psi	ASTM D790
Flexural Modulus	9.9133 GPa	1437.8 ksi	ASTM D790
Izod Impact, Notched	0.641 J/cm	1.20 ft-lb/in	ASTM D256
Izod Impact, Unnotched	7.47 J/cm	14.0 ft-lb/in	ASTM D4812

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	253 °C	487 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	239 °C	462 °F	ASTM D648

Processing Properties	Metric	English	Comments
Melt Temperature	290 - 310 °C	554 - 590 °F	
Mold Temperature	65.6 - 93.3 °C	150 - 200 °F	
Drying Temperature	79.4 °C	175 °F	
Dry Time	2 - 4 hour	2 - 4 hour	Predrying

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China