

## A. Schulman SCHULAMID® 66 MK30HI 30% Mineral Reinforced, Impact Modified Nylon 66

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, 30% Mineral Filled

**Material Notes:**

Information provided by A. Schulman.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_A-Schulman-SCHULAMID-66-MK30HI-30-Mineral-Reinforced-Impact-Modified-Nylon-66.php](http://www.lookpolymers.com/polymer_A-Schulman-SCHULAMID-66-MK30HI-30-Mineral-Reinforced-Impact-Modified-Nylon-66.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.36 g/cc	1.36 g/cc	ASTM D792
Linear Mold Shrinkage	0.0040 - 0.014 cm/cm @Thickness 3.175 mm	0.0040 - 0.014 in/in @Thickness 0.1250 in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	80.0 MPa	11600 psi	ASTM D638
Tensile Modulus	4.299 GPa	623.5 ksi	ISO 527

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	205 °C	401 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	120 °C	248 °F	ASTM D648

Processing Properties	Metric	English	Comments
Melt Temperature	295 - 305 °C	563 - 581 °F	
Mold Temperature	65.6 - 93.3 °C	150 - 200 °F	
Drying Temperature	79.4 °C	175 °F	
Dry Time	2 - 4 hour	2 - 4 hour	Predrying

### Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China