

## ACC MM820 Low Tear Condensation Cure 2-Part Molding Rubber

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE) , Silicone

### Material Notes:

Part of the Amber Chemical Group. Data provided by manufacturer. Characteristics: low viscosity, good resistance to styrene attack, easy degassing, low shrinkage, range of catalysts. Applications: shoe sole moulding, leather reproduction, moulds without undercuts.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_ACC-MM820-Low-Tear-Condensation-Cure-2-Part-Molding-Rubber.php](http://www.lookpolymers.com/polymer_ACC-MM820-Low-Tear-Condensation-Cure-2-Part-Molding-Rubber.php)

Physical Properties	Metric	English	Comments
Viscosity	6000 cP	6000 cP	

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	20	20	
Tensile Strength, Yield	1.00 MPa	145 psi	
Elongation at Break	250 %	250 %	
Tear Strength	2.50 kN/m	14.3 pli	

Descriptive Properties	Value	Comments
Color	White	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China