

## AK Steel 17-4 PH® Precipitation Hardening Stainless Steel, Condition H 1150-M

Category : Metal , Ferrous Metal , Martensitic , Stainless Steel , Precipitation Hardening Stainless

### Material Notes:

AK Steel 17-4 PH® provides an outstanding combination of high strength, good corrosion resistance, good mechanical properties at temperatures up to 600°F (316°C), and good toughness in both base metal and welds. Short-time, low-temperature heat treatments minimize distortion and scaling. This alloy is widely used in the aerospace, chemical, petrochemical, food processing, paper and general metalworking industries. The material supplied from the mill is in Condition A. After fabrication eight standard heat treatments have been developed to provide a wide range of properties. Information provided by AK Steel

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_AK-Steel-17-4-PH-Precipitation-Hardening-Stainless-Steel-Condition-H-1150-M.php](http://www.lookpolymers.com/polymer_AK-Steel-17-4-PH-Precipitation-Hardening-Stainless-Steel-Condition-H-1150-M.php)

Physical Properties	Metric	English	Comments
Density	7.80 g/cc	0.282 lb/in <sup>3</sup>	Typical

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell C	33	33	
Tensile Strength, Ultimate	1034 MPa	150000 psi	
Tensile Strength, Yield	896 MPa @Strain 0.200 %	130000 psi @Strain 0.200 %	
Elongation at Break	12 %	12 %	in 2 inches

Component Elements Properties	Metric	English	Comments
Carbon, C	<= 0.070 %	<= 0.070 %	
Chromium, Cr	15 - 17.5 %	15 - 17.5 %	
Copper, Cu	3.0 - 5.0 %	3.0 - 5.0 %	
Iron, Fe	69.91 - 78.85 %	69.91 - 78.85 %	As Remainder
Manganese, Mn	<= 1.0 %	<= 1.0 %	
Nb + Ta	0.15 - 0.45 %	0.15 - 0.45 %	
Nickel, Ni	3.0 - 5.0 %	3.0 - 5.0 %	
Phosphorous, P	<= 0.040 %	<= 0.040 %	
Silicon, Si	<= 1.0 %	<= 1.0 %	
Sulfur, S	<= 0.030 %	<= 0.030 %	

Component Elements Properties

Metric

English

Comments

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China